

Appl. No. 09/321,323
Filed: August 2, 2001
Page 2

Amendments to the Claims:

1. (Previously Presented) A process for producing spunbond nonwoven fabric, comprising the steps of:

separately melting two or more polymeric components, at least one polymeric component including reclaimed polypropylene recovered from previously spun polypropylene fiber or webs comprised of previously spun polypropylene fiber;

separately directing the two or more molten polymer components through a distribution plate configured so that the separate molten polymer components combine at a multiplicity of spinnerette orifices to form bicomponent filaments containing the two or more polymer components, the polymer components being arranged in a sheath-core cross-sectional configuration, with the polymer component containing reclaimed polypropylene being present in the core, and the reclaimed polypropylene being in an amount up to 100% by weight, and with the total amount of reclaimed polypropylene in the filaments being 25% by weight or greater;

extruding the multicomponent filaments from the spinnerette orifices into a quench chamber;

directing quench air from a first independently controllable blower into the quench chamber and into contact with the filaments to cool and solidify the filaments;

directing the filaments and the quench air into and through a filament attenuator and pneumatically attenuating and stretching the filaments;

directing the filaments from the attenuator into and through a filament depositing unit;

depositing the filaments from the depositing unit randomly upon a moving continuous air-permeable belt to form a nonwoven web of substantially continuous filaments;

applying suction from a second independently controllable blower beneath the air-permeable belt so as to draw air through the depositing unit and through the air-permeable belt; and

Appl. No. 09/321,323
Filed: August 2, 2001
Page 3

directing the web through a bonder and bonding the filaments to convert the web into a coherent nonwoven fabric.

2. (Cancelled)

3. (Cancelled)

4. (Previously Presented) The process according to Claim 1, wherein the polymeric component forming the core is formed entirely of said reclaimed polypropylene.

5. (Original) The process according to Claim 4, wherein the sheath is formed entirely of virgin polypropylene.

6. (Original) The process according to Claim 4, wherein the sheath is formed of a blend of virgin polypropylene and reclaimed polypropylene recovered from previously spun polypropylene fiber or webs comprised of previously spun polypropylene fiber.

7. (Previously Presented) A process for producing a spunbond nonwoven fabric, comprising the steps of:

separately melting a first polymeric component comprising virgin polypropylene and a second polymeric component comprising reclaimed polypropylene recovered from previously spun polypropylene fiber or webs comprised of previously spun polypropylene fiber;

separately directing the first and second molten polymer components through a distribution plate configured so that the separate molten polymer components combine at a multiplicity of spinnerette orifices to form bicomponent filaments containing a core of the second polymer component and a surrounding sheath of the first polymer component, with the core containing reclaimed polypropylene in an amount up to 100% by weight,

Appl. No. 09/321,323
Filed: August 2, 2001
Page 4

and with the total amount of reclaimed polypropylene in the filaments being 25% or greater;

extruding the bicomponent filaments from the spinnerette orifices into a quench chamber;

directing quench air from a first independently controllable blower into the quench chamber and into contact with the filaments to cool and solidify the filaments;

directing the filaments and the quench air into and through a filament attenuator and pneumatically attenuating and stretching the filaments;

directing the filaments from the attenuator into and through a filament depositing unit;

depositing the filaments from the depositing unit randomly upon a moving continuous air-permeable belt to form a nonwoven web of substantially continuous filaments;

applying suction from a second independently controllable blower beneath the air-permeable belt so as to draw air through the depositing unit and through the air-permeable belt; and

directing the web through a bonder and bonding the filaments to convert the web into a coherent nonwoven fabric.

8. (Original) A process according to Claim 7, wherein the second polymer component has a melt flow rate at least 5 units greater than that of the first polymer component.

9. (Original) A process according to Claim 7, wherein the core is formed entirely of said reclaimed polypropylene.

10. (Previously Presented) A process for producing a spunbond nonwoven fabric, comprising the steps of:

reclaiming polypropylene from previously spun polypropylene fiber or webs comprised of previously spun polypropylene fiber;

Appl. No. 09/321,323
Filed: August 2, 2001
Page 5

separately melting a first polymeric component comprising virgin polypropylene and a second polymeric component comprising the reclaimed polypropylene;

separately directing the first and second molten polymer components through a distribution system configured so that the separate molten polymer components combine at a multiplicity of spinnerette orifices to form bicomponent filaments containing a core of the second polymer component and a surrounding sheath of the first polymer component, with the core containing reclaimed polypropylene in an amount up to 100% by weight, and with the total amount of reclaimed polypropylene in the filaments being 25% by weight or greater;

extruding the bicomponent filaments from the spinnerette orifices into a quench chamber;

directing quench air into the quench chamber and into contact with the filaments to cool and solidify the filaments;

directing the filaments and the quench air into and through a filament attenuator and pneumatically attenuating and stretching the filaments;

directing the filaments from the attenuator into and through a filament depositing unit;

depositing the filaments from the depositing unit randomly upon a moving continuous air-permeable belt to form a nonwoven web of substantially continuous filaments; and

directing the web through a bonder and bonding the filaments to convert the web into a coherent nonwoven fabric.

11 - 28. (Cancelled)